

TETRASTAR STYLE 4908



Style 4908 restructured PTFE gasket material is a blend of barium sulphate dispersed throughout the PTFE. This general purpose grade is well suited for applications involving hydrofluoric acid, alkalis, solvents, fuels, and many other medias.

Tetra-Star Style 4908

Properties	Test Method	Results
pH Range		0 - 14
Applicable Pressure		83
Applicable Temperature		-328 to 500°F
Tensile Strength	ASTM 152	14
Density	ASTM D792	2.90
Compressibility	ASTM F36A	4-10
Recovery	ASTM F36A	40
Leakage (ml/h)	ASTM F37A	
Creep Relaxation	ASTM F38	11
Color		Off-White
Sheet Size		59" x 59"
Sheet Thickness		1/64, 1/32, 1/16, 3/32, 1/8